

DABEDAN

TEJIDOS IGNÍFUGOS

RENO

NIZA

| | | |
|---|--|--|
| Ancho / Width / Largeur | 145 cm | 140 cm |
| Composición / Composition / Support: | 40 % Trevira CS / 60 % Pes FR | 62 % Trevira CS / 38 % Pes FR |
| Clasificació FR / Classment FR / FR Class: | M-1 C-1 (UNE EN 13773:2003) | M-1 C-1 (UNE EN 13773:2003) |
| Peso / Weight / Poids: | 380 gr/m +/-5% (UNE EN 12.127) | 500 gr/m +/-5% (UNE EN 12.127) |
| Solidez a la luz / Light fastness / Solidité lumière: | 4 - 5 (UNE- EN ISO 105-B02:2013-2) | 4 - 5 (UNE- EN ISO 105-B02:2013-2) |
| Resistencia a la abrasión / Abrasion resistance / Résistance à l'abrasion | > 60.000 c (UNE EN ISO 12947: 1999) | > 100.000 c (UNE EN ISO 12947: 1999) |
| Pilling | Clase A (UNE EN ISO 12945-2) | Clase A (UNE EN ISO 12945-2) |
| Resistencia a la Tracción / Résistance à la Traction / Breaking Strength | Warp: 1.200 Weft: 1.150 (UNE EN ISO 13934-1 2013) | Warp: 1.300 Weft: 1.160 (UNE EN ISO 13934-1 2013) |
| Absorción acústica / Sound absorption / Absorption acoustique | $\alpha = 0.70$ (H) Clase C (UNE-EN ISO 354:2004) | $\alpha = 0.70$ (H) Clase C (UNE-EN ISO 354:2004) |



RECYCLABLE

▶ Las características técnicas especificadas en el presente documento tienen valor únicamente informativo careciendo de carácter vinculante. El fabricante se reserva el derecho de introducir modificaciones en cualquier momento por razones evolutivas de producto o de mercado. El color puede variar de una partida a otra.

▶ *The technical characteristics specified in this document are strictly informative and not guaranteed. The manufacturer reserves the right to introduce modifications at its discretion at any time. Colour may vary from batch to another.*

Si necesita una muestra de color de 20 x 20 cm. por favor, solicítela a su proveedor habitual. Se la enviaremos al momento.

If you need any colour sample of 20 x 20 cm., do not hesitate in asking for it at his habitual supplier. We shall send it at once.



OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100 